

## Sure Klean<sup>®</sup> Limestone & Masonry Afterwash Cleaning Specification

*Specifier Note: The information provided below is intended to guide the Architect in developing specifications for products manufactured by PROSOCO, Inc. and should not be viewed as a complete source of information about the product(s). The Architect should always refer to the Product Data Sheet and MSDS for additional recommendations and for safety information. See also PROSOCO Section 04900 Masonry Restoration & Cleaning.*

*Specifier Note: Paragraph below is for PART 1 GENERAL, Quality Assurance.*

### Test Area

Test a minimum 4 ft. by 4 ft. area on each type of masonry. Use manufacturer's application instructions. Let the test panel dry 3 to 7 days before inspection. Keep test panels available for comparison throughout the cleaning project.

*Specifier Note: Paragraphs below are for PART 2 PRODUCTS, Manufacturers and Products.*

**Manufacturer:** PROSOCO, Inc., 3741 Greenway Circle, Lawrence, KS 66046. Phone: (800) 255-4255; Fax: (785) 830-9797. E-mail: [CustomerCare@prosoco.com](mailto:CustomerCare@prosoco.com)

### Product Description

Sure Klean<sup>®</sup> Limestone & Masonry Afterwash is a mild organic acid cleaning compound that neutralizes and brightens surfaces that have been prewashed with Sure Klean<sup>®</sup> 766 Limestone & Masonry Prewash and Enviro Klean<sup>®</sup> BioKlean<sup>™</sup>. When used properly, these two-part cleaning systems remove heavy carbon, dirt and other atmospheric stains from porous limestone, concrete and most other porous masonry surfaces. As part of the BioKlean<sup>™</sup> system, Limestone & Masonry Afterwash helps remove combinations of atmospheric and biological staining that blacken limestone, marble, concrete and other masonry surfaces in humid environments. Limestone & Masonry Afterwash will not damage most masonry surfaces when used properly.

### Technical Data

FORM: Clear liquid, with pungent, vinegar-like odor  
SPECIFIC GRAVITY: 1.02  
FLASH POINT: >200 degrees F (>93 degrees C) (ASTM D 93)  
pH: 1.10 (concentrate)  
FREEZE POINT: 9 degrees F (-13 degrees C)  
WT./GAL.: 8.50 lbs.

### Limitations

- On severely stained brick, terra cotta, sandstone or granite, improved cleaning results may be achieved with an alternative Sure Klean<sup>®</sup> afterwash. Following use of Sure Klean<sup>®</sup> 766 Limestone & Masonry Prewash, test Sure Klean<sup>®</sup> Light Duty Restoration Cleaner, Restoration Cleaner or Heavy Duty Restoration Cleaner to determine the most effective cleaning system.

*Specifier Note: Paragraphs below are for PART 3 EXECUTION, Installation.*

### Application

Before applying, read "Protect" and "Precautionary Measures" sections in the Manufacturer's Product Data Sheet for Limestone & Masonry Afterwash. Dilute 1 part water to 1 part concentrate.

Use Limestone & Masonry Afterwash as a follow-up treatment to Sure Klean<sup>®</sup> 766 Limestone and Masonry Prewash and Enviro Klean<sup>®</sup> BioKlean<sup>™</sup>. Limestone & Masonry Afterwash works as part of these two-part cleaning systems to completely restore and neutralize masonry surfaces.

1. Immediately after rinsing 766 Limestone & Masonry Prewash or BioKlean<sup>™</sup> from masonry surface, apply the diluted Afterwash to the wet surface.
2. Let the Afterwash stay on the surface for three to five minutes.
3. Pressure rinse from the bottom of the treated area to the top. Make sure to cover each portion of the masonry surface with a concentrated stream of water. To avoid streaking, keep wall surfaces immediately below area being cleaned running wet and free of cleaner rundown and residues.